


Endurans™ backsheet

Endurans™ HP D15BE

Features and benefits

- For mainstream applications - with outstanding UV and abrasion resistance in its class
- Good moisture barrier and hydrolysis resistance due to strong polyolefins
- Designed for 1500V/1000V systems
- Co-extruded, fluorine-free and fully recyclable
- Black inner layer



Technical properties

	Test item	Unit	Test method	Typical values D15BE
Basic properties	Total thickness	µm	Caliper	350
	Inter layer strength	N/10mm	ASTM D1876	Cannot peel off
	Heat shrinkage (MD)	%	150 °C*30min	0.4
	Heat shrinkage (TD)	%	150 °C*30min	0.4
	Elongation at break (MD)	%	IEC 62788-2: 2017	800
	Elongation at break (TD)	%	IEC 62788-2: 2017	800
	Peel strength with EVA	N/10mm	ASTM D1876	Cannot peel off
	Breakdown voltage	kV	ASTM D1868	24
	CTI	V	IEC 60112	600
	DTI	µm	IEC 61730-1	320
	WVTR (38 °C, 90RH%)	g/m ² *day	ASTM 1249	0.6
Durability performance	Pressure cook test 96h (121 °C, 100RH%, 0.2 MPa)		IEC 60068-2-66	no bubble no delamination no cracks elongation retention>60%
	Damp heat 2000h		IEC 61215	
	UV exposure 300 kWh/m ²		IEC 61215	

Note: all values stated herein are to be considered as typical values.

Protect PV performance with Endurans™ backsheet technology. Built to last.

More information:

info@endurans.com or www.endurans.com

IMPORTANT NOTICE:

Endurans™ Solar believes the information on this sheet to be reliable but does not guarantee its accuracy of completeness. Conduct your own tests of this product to determine its suitability for intended use. User assumes all risks and liability during testing and use of this product. The only obligation of Endurans™ Solar and its distributors shall be to replace any of this product proved to be defective in material or workmanship. Neither Endurans™ Solar nor its distributors shall be liable for any injury, loss or damage, direct or consequential, relating to the use or inability to use this product. Except as expressly provided above, all products are sold and samples furnished without any warranty of merchantability or any other warranty, expressed or implied.
21.001 © Endurans™ Solar 2021



Same sun.
More power.TM

